

Chemical Resistance



The information contained in the document is property of Avanti International. Avanti offers the following verbiage as a technical reference to assist in the education of chemical grouting contractors and government agencies in addition to the creation of specifications for chemical grouting.

Chemical Resistance of AV-202 Multigrout

Chemical % Water	Time (Weeks)	Visual Appearance
Hydrochloric 2%	26	Moderate darkening and slight fragmentation
Acetic 2%	26	No Change
Sulfuric 2%	26	Moderate darkening – intact
Potassium Hydroxide 1%	26	Moderate darkening – 25% dissolved
Salts		
Sodium Chloride (salt water)	26	No Change
Ammonium Sulfate (2%)	26	No Change
Potassium Chlorate (5%)	26	No Change
Isopropanol 100%	26	No Change
Heptane 100%	26	No Change
Carbon Tetrachloride 100%	26	Slight darkening
Methyl Ethyl Ketone 100%	26	Swelled 20-30%
Toluene 100%	26	No Change
Hydrogen Sulfide Gas 100% wet condition	9	No Change
Hydrogen sulfide Gas 80% wet condition	10	No Change