AVANTI
Stop leaks. Stabilize soil.
Control groundwater. Permanently.

TECHNICAL DATA SHEET

AV-202-LV Multigrout LV™

Hydrophilic Polyurethane Grout

Description

AV-202-LV Multigrout LV™ is the low viscosity version of the original AV 202® Multigrout. It is a versatile, single-component polyurethane injection resin formulated with an MDI/TDI blend. AV-202-LV is activated by moisture and engineered to seal active water leaks by permeating tight cracks or joints in poured concrete, pipe penetrations, or precast structures. AV-202-LV forms a strong, impermeable bond with excellent adhesion when mixed at a 1:1 water-to-resin ratio or turns into a gel at an 8:1 ratio.

Applications

- Cracks or joints in concrete, or used in conjunction with AV-215 Resin Rod™ or AV-219 Fibrotite™ (Oakum)
- Designed for applications where high-volume water flow is an active and/or potential problem, subgrade or wet environments cracks or joints, or where a high viscosity chemistry is required
- Used successfully in manhole sealing and pipe penetrations
- Excellent choice for moving cracks and joints

Features & Benefits

- Low viscosity version of the original AV-202® Multigrout
- 100% solids
- Free rise expands 300% – 600%
- Solvent-free and non-corrosive
- Cures flexible with superb adhesive properties
- Can accept up to 8X its volume in water
- Can be used in underwater applications
- Multiple grouting techniques including Expanded Gasket Placement Technique (EGP), Needle Penetration Technique (NPT), and Variable Pressure Application Technique (V-PAT) – Crack Injection

How AV-202-LV Works

AV-202-LV reacts with moisture to form a durable, flexible seal accomplished by three mechanisms. First the resin seeks out water in the space and pores of the substrate and adheres to the surface. Second, the resin/water reaction begins to expand forming a tight compressive seal and third the network of compressed grout material within all the cracks establishes a mechanical lock. The preferred ratio is 1:1 (water to resin), however it is effective up to a ratio of 8:1 with water. AV-202-LV may be pumped as a single component without pre-mixing.

Optional Products

- AV-203 Multicat™ – cream and gel time accelerator

Packaging – product is packaged by weight and is based on specific gravity (net wt.)

Grout

- Cartridge - ~10.1 fl. oz. (~ 300 ml), Case of 12 ea.
- Container – 8.8 lbs. (4.0 kg)
- Pail – 44 lbs. (20 kg)
- Drum – 484 lbs. (220 kg)

Optional Catalyst – AV-203

- Container - 78 fl. oz. (2.31 L)

Rev. 07.2026

AVANTI
Stop leaks. Stabilize soil.
Control groundwater. Permanently.

TECHNICAL DATA SHEET

Physical Properties*

UNCURED	
Appearance	Brown resin
Viscosity (water=1)	500 - 800 cP @ 72°F (22°C)
Flash Point	>200°F (>93°C)
Specific Gravity (water=1)	1.078 @ 72°F (22°C) ± 3%
Density	9.0 lbs./gal (1,078 kg/m^3) ± 3%
CURED	
Appearance	Milky colored, flexible
Tensile Strength	*Consult Avanti Representative*
Elongation	

** Laboratory results*

Performance - General

Gently shake or stir container(s) before using. For the best results, use AV-202-LV between 60°F – 90°F (16°C – 32°C). Performance will be influenced by site conditions. If site temperatures are low, use a heat source to warm to ~72°F (22°C) and apply. Do not use open flame as a heat source. At temperatures of 45°F (7°C), the viscosity of the product can significantly increase, making the miscibility with the reaction-water more difficult. The times presented are laboratory results. Actual results may be different in the field due to site water used or site conditions. Perform a standard cup test with site water to determine the desired reaction time.

Performance Using AV-202-LV

See Table below for approximate Cream/Gel Times for AV-202-LV

Cream / Gel (Cure) Times for AV-202-LV Multigrout LV (Min:Sec)*[1,2]				
		1:1 Water/AV-202-LV	**5:1 Water/AV-202-LV**	**8:1 Water/AV-202-LV**
Temperature	**40°F/4°C**	0:38 / 3:08	2:18	3:41
	50°F/10°C	0:28 / 1:46	1:11	1:45
	60°F/15°C	0:25 / 1:24	1:02	1:25
	70°F/21°C	0:20 / 1:12	0:52	1:13
	80°F/27°C	0:15 / 1:06	0:44	0:51

**Laboratory results*

Note: Cream time is not applicable with grout to water ratios above 1:1.

1. *Resin and water temperatures may affect cream / gel times.*
2. *Actual results may be different in the field due to site water used or site conditions.*

822 Bay Star Blvd. Webster, TX 77598 USA | 800.877.2570 | support@avantigrout.com | avantigrout.com

AVANTI
Stop leaks. Stabilize soil.
Control groundwater. Permanently.

TECHNICAL DATA SHEET

Performance When Adding AV-203 Multicat

Note: AV-203 should NOT be used when injecting at ratios higher than 1:1 water to AV-202-LV.

AV-203 Multicat may be used at low temperatures and/or high flow water cut-off situations at a maximum of 78 fl. oz. of AV-203 per pail of AV-202-LV. When AV-203 is used with AV-202-LV to slow down high waterflows, it should not be used as a stand-alone solution but in conjunction with any of Avanti's injection grouts. See Table below for approximate Cream/Gel Times for AV-202-LV used with AV-203.

Cream / Gel (Cure) Times for AV-202-LV Multigrout LV + AV-203 Multicfat (Min:Sec)*[1,2]			
		1:1 Water/AV-202-LV + Half Catalyst (Resin:Catalyst, 16:1)	**1:1 Water/AV-202-LV + Full Catalyst (Resin:Catalyst, 8:1)**
Temperature	**40°F/4°C**	0:20 / 1:03	0:17 / 0:48
	50°F/10°C	0:15 / 0:49	0:13 / 0:39
	60°F/15°C	0:12 / 0:40	0:11 / 0:34

**Laboratory results*

Note: Cream time is not applicable with grout to water ratios above 1:1. Do not use more than one container of AV-203 catalyst per pail of AV-202-LV.

1. Resin and water temperatures may affect cream / gel times.

2. Actual results may be different in the field due to site water used or site conditions.

Cleaning

Do not use water to clean equipment. AV-202-LV is water activated and will setup or cure in your hoses and equipment. Flush with AV-284 Pump Wash™ to remove uncured resin in hoses and equipment. Purge equipment and hoses with AV-208 Technical Grade Acetone™ before use to remove any remaining AV-284 and moisture.

- AV-208 Technical Grade Acetone™– removes moisture from equipment
- AV-222 Cleaner™– removes cured resin from equipment
- AV-284 Pump Wash™ – removes uncured resin from pump hose

Storage

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep container tightly closed when not in use. Packaged under dry nitrogen to keep moisture out and extend shelf life. Storage of opened/partial containers at the lower range of the recommended storage temperature is not advised as moisture in the air above a partial container might condensate and might cause the grout to premature gel in the container. Avanti does not recommend storing full or partially filled containers of AV-202-LV that have been catalyzed or mixed with AV-203. Catalyzed grout may react over time or if not stored correctly.

Safety

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The Safety Data Sheets and Mixing Guidelines are available 24/7 at avantigrout.com.

Shipping – Motor and Air Freight available

- Not regulated under US DOT Regulations

Notice

The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE. In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.

822 Bay Star Blvd. Webster, TX 77598 USA | 800.877.2570 | support@avantigrout.com | avantigrout.com

AVANTI
Stop leaks. Stabilize soil.
Control groundwater. Permanently.

TECHNICAL DATA SHEET

822 Bay Star Blvd. Webster, TX 77598 USA | 800.877.2570 | support@avantigrout.com | avantigrout.com