AVANTI
Stop leaks. Stabilize soil.
Control groundwater. Permanently.

TECHNICAL DATA SHEET

AV-258-MV PermaFlex™
with AV-259-MV PermaFlex AC™ Catalyst
Hydrophobic Polyurethane Grout

AV-258-MV PermaFlex™ is tested and certified by WQA against NSF/ANSI/CAN 61 Drinking Water System Components
For product use restrictions visit www.wqa.org

Description
AV-258-MV PermaFlex™ is a moisture activated MDI-based polyurethane resin. The water/moisture activation is a two-step chemical reaction and is catalyzed by mixing AV-259-MV PermaFlex AC™ with AV-258-MV. Injected as a single component, AV-258-MV is designed to react quickly with moisture to seal active and potential water leaks in cracks or small annular spaces that are susceptible to wet/dry cycles and where flexibility is needed. AV-258-MV should always be injected into small, narrow, confined spaces to provide restricted expansion of the grout. AV-258-MV cures flexible and impermeable.

Applications
- For use above or below grade in humid or arid atmospheres
- Fills various cracks and pipe penetrations
- Stops leaks in concrete structures
- Designed for tunnels, mines, dams, reservoirs, block walls and structures that may shift

Features & Benefits
- Free rise expands 700% – 1,200%
- Controllable reaction time by adjusting the amount of AV-259-MV PermaFlex AC
- Withstands wet/dry cycles
- Multiple grouting techniques including Expanded Gasket Placement Technique (EGP) and Variable Pressure Application Technique (V-PAT) – Crack Injection
- Tested and certified by WQA against NSF/ANSI/CAN 61 Drinking Water System Component

Required Products
- AV-259-MV PermaFlex AC™ (catalyst)

How AV-258-MV Works
AV-258-MV uncured resin must be injected into a confined space. Fill the space of the crack/joint with unreacted resin. The resin will react with moisture to form a resilient seal accomplished by three mechanisms: first the resin seeks out water in the space and pores of the substrate and adheres to the surface. Second, the resin/water reaction begins to expand forming a tight compressive seal in the confined space and third the network of compressed grout material within all the cracks establishes a mechanical lock. NOTE: Moisture activated resins require a minimum amount of water/moisture. If little or not enough water/moisture is present in the crack/joint to be sealed, water should be flushed through the crack/joint prior to injecting AV-258-MV.

Packaging – product is packaged by net weight

Grout
- Jug – 8.8 lbs. (4 kg)
- Pail – 44 lbs. (20 kg)
- Drum – 484 lbs. (219.5 kg)

Catalyst
- Container - 32 fl. oz. (.95 L)

Physical Properties*

UNCURED AV-258-MV	
Appearance	Milky white to clear liquid
Viscosity (water=1)	450 – 650 cP @ 72°F (22°C)
Flash Point	>200°F (>93°C)
Specific Gravity (water=1)	1.073 @ 72°F (22°C) ±3%
Density	8.95 lbs./gal. ± 3% (1.073 kg/L ± 3%)
CURED AV-258-MV	
Appearance	Milky white, flexible

Rev. 10.2026

Tensile Strength	*Consult Avanti Representative*
Toxicity	Non-toxic
AV-259-MV	
Appearance	Light yellow to white, clear liquid
Viscosity (water=1)	15 - 25 cP @ 72°F (22°C)
Flash Point	>200°F (>93°C)
Specific Gravity	1.015 @ 72°F (22°C) ±3%
Density	8.47 lbs./gal. ± 3% (1.015kg/L ± 3%)

** Laboratory results*

Mix Guidelines

Gently shake or stir container(s) before using. Typically, one container of AV-259-MV is used per pail of AV 258-MV PermaFlex. Depending on the desired reaction time, AV-259-MV may be doubled or tripled (see Cream / Gel (Cure) Times Chart below). Mix thoroughly, but slowly, to avoid creating bubbles in the solution.

Cream / Gel (Cure) Times for AV-258-MV PermaFlex (Min:Sec)					
		Half Catalyst (16 oz.) 40:1	**Full Catalyst (32 oz.) 20:1**	**Double Catalyst (64 oz.) 10:1**	**Triple Catalyst (96 oz.) 6.6:1**
Temperature	40°F/4°C	0:39 / 3:06	0:28 / 2:41	0:20 / 2:37	0:17 / 2:01
	50°F/10°C	0:32 / 2:54	0:24 / 2:27	0:18 / 2:07	0:14 / 1:58
	60°F/15°C	0:27 / 2:18	0:22 / 2:10	0:15 / 1:58	0:14 / 1:55
	70°F/21°C	0:23 / 2:16	0:20 / 2:03	0:15 / 1:51	0:12 / 1:48
	80°F/27°C	0:21 / 2:00	0:17 / 2:00	0:14 / 1:11	0:10 / 0:52

**Laboratory results*
Note: Do not use more than triple AV-259-MV catalyst per pail of AV-258-MV
1. *Resin and water temperatures may affect cream / gel times.*
2. *Actual results may be different in the field due to site water used or site conditions.*

Performance

For the best results, use AV-258-MV between 60°F – 90°F (16°C – 32°C). Flush equipment with AV-208 Technical Grade Acetone™ before and after use to remove moisture and clean equipment. Performance will be influenced by site conditions. If site temperatures are low, use a heat source to warm to ~72°F (22°C) and/or increase catalyst amount by 1% – 2%. Do not exceed more than 96 fl. oz. (3 L) of AV-259-MV per pail of the AV-258-MV resin. Do not use open flame as a heat source. At temperatures of 45°F (7°C), the viscosity of the product is significantly increased, making the miscibility with the reaction-water more difficult. Excess amounts of AV-259-MV may adversely affect performance. Catalyzed resin will react with moisture from the air, use product soon after mixing. The times presented are laboratory results. Actual results may be different in the field due to site water used or site conditions. Perform a standard cup test with site water to determine the desired reaction time.

Cleaning

Do not use water to clean equipment. AV-258-MV is water activated and will setup or cure in your hoses and equipment. Flush with AV-284 Pump Wash™ to remove uncured resin in hoses and equipment. Purge equipment and hoses with AV-208 Technical Grade Acetone™ before use to remove any remaining AV-284 and moisture.

- AV-208 Technical Grade Acetone™– removes moisture from equipment (see Performance section)
- AV-222 Cleaner™– removes cured resin from equipment
- AV-284 Pump Wash™ – removes uncured resin from pump hose

Storage
Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep container tightly closed when not in use. Packaged under dry nitrogen to keep moisture out and extend shelf life. Storage of opened/partial containers at the lower range of the recommended storage temperature is not advised as moisture in the air above a partial container might condensate and might cause the grout to premature gel in the container. Avanti does not recommend storing full or partially filled containers of AV-258-MV that have been catalyzed or mixed with AV-259-MV. Catalyzed grout may react over time or if not stored correctly.

Safety
Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The Safety Data Sheets and Mixing Guidelines are available 24/7 at avantigrout.com.

Shipping – Motor and Air Freight available

- Not regulated under US DOT Regulations

Notice
The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE. In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.

822 Bay Star Blvd. Webster, TX 77598 USA | 800.877.2570 | support@avantigrout.com | avantigrout.com