



TECHNICAL DATA SHEET

AV-102[®] CATALYST AP

AMMONIUM PERSULFATE / INITIATOR

DESCRIPTION

AV-102 Catalyst AP (often referred to as AP) is a white crystalline solid used as the initiator for the radical polymerization reaction of acrylic and acrylate monomers. Ammonium persulfate is a powder that is a required grout component for **AV-100[®]** Chemical Grout or **AV-118[®]** Duriflex and can be increased from 5 lbs. (1% by total mix weight of 500 lbs) to a maximum of 15 lbs. (3% by total mix weight of 500 lbs). When used with **AV-150** Acrylate Gel™ or **AV-160** Supergel™, the amount of **AV-102** is from 10 lbs. to a maximum of 30 lbs. (6% by weight). **AV-102** is a strong oxidizing material which decomposes over time.

USED WITH

- **AV-100** Chemical Grout
- **AV-118** Duriflex
- **AV-150** Acrylate Gel
- **AV-160** Supergel
-

PACKAGING

Product packaged by weight based on specific gravity.

Net Wt.

Pail 50 lbs. (22.6 kg)

Drum 220 lbs. (99.7 kg)

SHIPPING

- Motor Class 65
- Hazard Class 5.1
- Air freight available

CLEANING PRODUCTS

Use water with light detergent.

PROPERTIES*

Appearance:	White crystals
Viscosity:	1-2 cP in solution
pH:	4 – 6 (1% solution)
Boiling Point:	Decomposes > 212°F (100°C)
Melting Point:	Decomposes > 212°F (100°C)
Flash Point:	Non-flammable
Specific Gravity (water=1)	1.98
Solubility:	85% by weight @ 77°F (25°C) *Laboratory Results

MIX PROCEDURE FOR STANDARD MIX

When mixing with **AV-100** (Tank A), add 5 lbs. of **AV-102** to Tank B. When adding additional **AV-101** to Tank A, an equal amount of **AV-102** should be added to Tank B. See complete mixing instructions at avantigrout.com.

IMPORTANT: **AV-102** dissolved in water loses its effectiveness rapidly at elevated temperatures.

STORAGE

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere and keep the lid closed. Elevated temperatures and moisture will degrade AP. Keep away from reducing agents like **AV-101**.

SAFETY

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS is available by request or via download at avantigrout.com.

NOTICE

The data, information and statements contained herein are believed to be reliable, but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.